

SYNTHO-GLOSS[®] XT

EXTREME STRENGTH FIBERGLASS COMPOSITE SYSTEM



Description

Syntho-Gloss[®] XT system is a unique pre-impregnated, bidirectional composite used to repair and reinforce both internal and external corrosion on pipelines or structures without expensive and time consuming shutdowns. Our pre-preg system ensures proper fiber-to-resin content ratios which are crucial to reliable performance. The initial development of this system was designed to conform to both the ASME PCC-2 and ISO TS24817 standards for nonmetallic reinforcing solutions. This extreme strength design minimizes the time and cost of refurbishment by reducing the time to repair, as well as the replacement cost. When used with the appropriate primary coating, it enables one to repair and reinforce virtually any geometry in minutes.

Mechanical Properties

Test	Method	Result
Tensile Strength	ASTM D3039	Hoop: 54,000 psi (3724.0 bar) Axial: 34,000 psi (2344.8 bar)
Hardness, Shore D @ 75°F (24°C)	ASTM D2240	83
Flexural Strength	ASTM D790	58,680 psi (4046.8 bar)
In-Plane Shear Strength	ASTM D5379	7,520 psi (518.6 bar)
CTE	ASTM D648	Hoop: CTLE: 1.06E-05 inches/inches/°F
Lap Shear	ASTM D3163	2,000 psi (137.8 bar)

Typical Applications

- Pipeline Integrity
- Transmission and distribution pipelines
- Oil and gas risers
- Girth welds on vessels and pipelines
- Elbows, tees, and flanges
- Process piping: chemicals, oil, gases, water, and steam
- Atmospheric corrosion

Benefits

- Water-activated urethane resin reduces composite preparation time by over 50%
- Installation in wet or submerged environments ensures ease of application in virtually any situation
- Simplicity and flexibility permit application to irregular shapes and geometries, thereby reducing parts inventory
- Full factory engineering consultation and support, ensuring safe and successful repairs
- Conformance to ASME PCC-2, DOT, ISO TS24817, CSA Z662, and API570, ensuring product application integrity

Physical Properties

VOCs: None

Working Time: 30 Minutes @ 75°F (24°C)

Initial Cure Time: 2 Hours @ 75°F (24°C)

Resin Type:

Water-activated, polyurethane

Resin Application:

Micro-controlled, Pre-impregnated

Service Temperature:

-50° to 194°F (-46° to 90°C)


Shelf Life: 12 months





Syntho-Glass XT System Components:

- Syntho-Poxy™HC: Reinforcing Load Transfer Epoxy
- Syntho-Subsea™LV: Kevlar® Reinforced Epoxy
- Syntho-Glass®UV: UV Protectant Coating
- Installation Accessory Kit: Compression film, film perforation tool, additional protective gloves, and epoxy applicator tools



Syntho-SubseaLV Epoxy Data

Test	Result
Tensile Strength	6,000 psi (413.68 bar)
Compression Strength	7,380 psi (508.83 bar)
Flexural Strength	4,550 psi (313.71 bar)
Flexural Modulus	142,188 psi (9803.51 bar)
Abrasion Resistance	34.0 mg/1,000 cycles (CS17 wheels with 1,000 gram weights)
Temperature	Result
Service Temperature: Dry Applications	-50°/275°F (-45°/135°C)
Service Temperature: Wet Applications	-50°/160°F (-45°/71°C)



©Neptune Research Inc. (NRI) NRI® and Syntho-Glass®XT are registered trademarks while Syntho-Subsea™ and Syntho-Poxy™HC are trademarks of NRI. NRI utilizes a process of continuous product improvement for all of our products. While we do strictly adhere to our products' specifications, we routinely implement product improvements. Therefore, please contact your local NRI distributor or office for the most current product specifications. NRI warrants the quality of this product when used according to directions. Syntho-Glass XT is NOT an approved coating system. Failing to coat per standard procedures can lead to atmospheric corrosion damage. Apply protective coatings per company standards. User shall determine suitability of product for use and assumes all risk. The seller will not accept liability for more than product replacement. SGXT DS 0711
Kevlar® is a registered trademark of E. I. du Pont de Nemours and Company.

