

SYNTHO-SUBSEA™ LV

LOW VISCOSITY, SELF LEVELING, UNDERWATER EPOXY MASTIC SEALANT SYSTEM



Description

Syntho-Subsea™ LV Epoxy is a unique blend of liquid epoxy, polymer, and aliphatic polyamine curing agents that is able to displace water from wet surfaces in order to make a permanent bond. The formulation is solvent-free to ensure safety and maximum technical performance. Kevlar® fibers are incorporated for reinforcement and viscosity management to achieve high-application rates – even underwater. Provides permanent protection under the most adverse conditions, the formula is uniquely field-friendly and uses advanced, low-toxicity ingredients in a high-build brushable/rollable product. Syntho-Subsea™ LV Epoxy can be shipped non-regulated by USDOT, IATA, and IMO.

Mechanical Properties

Test	Method	Result
Tensile Strength	ASTM D3039	6,000 psi (413.68 bar)
Compression Strength	ASTM D695	7,380 psi (508.83 bar)
Flexural Strength	ASTM D790	4,550 psi (313.71 bar)
Flexural Modulus	ASTM D790	142,188 psi (9803.51 bar)
Lap Shear Strength	ASTM D3163	1,782 psi (122.86 bar)
Abrasion Resistance	CS17 wheels with 1,000 gram weights	34.0 mg/1,000 cycles

Item #	Description
SUBLV_040Z	4 oz (197g) Bi-Pack
SUBLV_080Z	8 oz (394g) Bi-Pack
SUBLV_160Z	16 oz (787g) Bi-Pack
SUBLV2QT	2qt (1.892l) Kit contains 1qt A+1qt B
SUBLV.4G	0.4 gal (1.514l) cartridge, (A+B)
SUBLV2G	2 gal (7.570l) Kit contains 1gal A+1gal B
SUBLV10G	10 gal (37.854l) Kit contains 5gal A+5gal B

©Neptune Research Inc. (NRI) NRI® is a registered trademark, while Syntho-Subsea™ LV is a trademark of NRI. NRI utilizes a process of continuous product improvement for all of our products. While we do strictly adhere to our products' specifications, we routinely implement product improvements. Therefore, please contact your local NRI distributor or office for the most current product specifications. NRI warrants the quality of this product when used according to directions. User shall determine suitability of product for use and assumes all risk. The seller will not accept liability for more than product replacement. SSLV DS 0811

Typical Applications

- Anticorrosive Coating: Splash zone, excellent abrasion resistance above or below water.
- Repair Compound: Patching, coating repair, etc.
- Encapsulating Coating: Smooth, dense, easily decontaminated coating for steel and concrete.
- Wastewater: Reinforces, smoothes, and protects concrete exposed to chemical or municipal waste.

Physical Properties

VOCs: None

Service Temperature:

Dry: -50°/275°F (-45°/135°C)

Wet: -50°/160°F (-45°/71°C)

Mixing Ratio: 1:1 by volume

Pot Life at 77°F (25°C): 20 Minutes

Flash Point: Over 200°F (93°C)

Solids by Volume: 100%

Spreading Rate/Gallon:

1,604 mil/sq. ft.

53.5 sq. ft./30 mils

Cure Time at 77°F (25°C): 24 Hours

Storage Conditions: Normal, Freezing OK

Shelf Life: 24 Months

